F & F ASSEMBLIES INC.

TECHNICAL DATA SHEET

GLASTEEL Acrylit _{GC} HIGH STRENGTH FIBERGLASS PANELS FOR LAMINATION TO THE NBS CFR PANEL

Product Description: Consisting of an 8 OZ. 100 % Acrylic Translucent Panel Woven Roving Strand combined with chopped strand Matrix Fiberglass Reinforcement

PHYSICAL PROPERTIES

Property	ASTM Std.	Typical Values
TENSILE STRENGTH	D638	25,772 psi.
TENSILE MODULUS	D638	1.52 X10 ⁶ psi.
FLEXURAL STRENGTH	D790	24,306 psi.
FLEXURAL MODULUS	D790	0.79 X 10 ⁶ psi.
COMPRESSIVE STRENGTH	D695	28,905 psi.
SELF-IGNITION TEMPERATURE	D1929	GREATER THAN 650° F
*SMOKE DENSITY	E-84	<450
COMPRESSION MODULUS	D-695	1.5 X 10 ⁶ psi
*BURNING RATE	D-635	<2.5 in / min.
*UNIFORM BUILDING CODE	D-635	CC2
CLASSIFICATION		
BARCOL HARDNESS	D-2583	40-50
*LIGHT TRANSMISSION	D-1494	55-60
*U FACTOR (with Film Coefficients)	NFRC 102-2004	1.08 BTU/ Hr ft2°F
* LINEAR THERMAL EXPANSION	D-638 1.9	9* X 10 ⁻⁵ IN. / IN./ ⁰ F
BEARING STRENGTH	D-953	24.8 ksi (3.88)
WATER ABSORBTION	D-570	0.25% @ 72° F /72 hrs.
SOLAR HEAT GAIN	NFRC 201-2004	.45
*SOLAR ABSORBTANCE	E-903	77.73
*REFLECTANCE AND EMMITANCE	E-1371/E1918	.58 / .91
IZOD IMPACT	D-4812	18.59 Ft-lb / in ²
LUMINOUS TRANSMITTANCE	D 1003-07	77.18%
HAZE	D-1003-07	112.78 %
Tolerances:		
PANEL WEIGHT	+/-	10%
RIB HEIGHT		
LENGTH		
WIDTH		
SQUARENESS		
SQUARENESS		1/001

Codes and approvals:

ASTM-D3841 "Specifications for Glass Fiber-Reinforced Polyester Plastic
Panels"UL90 STAND ALONE APPROVAL BY UL FOR ANY TRAPEZOIDAL SYSTEM
Recognized Component File (#R5214)

ICBO#/ ICC ER-2364

The information offered herein is offered without charge and is accepted at recipient's sole risk. Because conditions of use vary and are beyond our knowledge and control, Glasteel makes no representation about and is not responsible for the accuracy of data, nor with toxicological effect or industrial hygiene requirements associated with particular uses of any product or process described herein. Glasteel requests that customers test and inspect our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of Glasteel materials only.